

Aldex MP Series

C-800H MP Macroporous Strong Acid Resin Hydrogen Form

Aldex C-800H MP is a **premium grade, high capacity, strongly acidic macroporous cation resin in the hydrogen form**, used in demineralization systems and condensate polishers. Aldex C-800H MP combines high capacity characteristics with the increased thermal and chemical stability versus gellular resins. Aldex C-800H MP is more highly crosslinked than our standard non-solvent resins Aldex C-800H and Aldex C-800x10H.

Physical Chemical Properties

Resin Composition:	Macroporous polystyrene crosslinked with divinylbenzene
Ionic Form as Shipped:	Hydrogen (H ⁺)
Physical Form:	Spherical particles
Moisture Content	
Na ⁺ Form:	48 to 53%
H ⁺ Form:	50 to 56%
Total Capacity	
Na ⁺ Form:	2.0 eq/l
H ⁺ Form:	1.8 eq/l
Odor and Taste:	None
Net Weight (as shipped):	50 lbs per cubic foot
Particle Size:	16 to 50 mesh
Uniform Coefficient	1.7 maximum

Recommended Operating Conditions

Influent pH:	0 to 14
Maximum Temperature:	300 °F
Bed Depth:	Minimum 36"
Service Flow Rate:	1 to 5 US gpm/ft ³ (8 to 40 BV/h)
Backwash Flow Rate:	See Fig. 2
Regenerant:	Hydrochloric Acid (HCl)
Regenerant Strength:	2 to 7%
Regenerant Flow Rate:	0.30 to 0.9 US gpm/ft ³ (2 to 7 BV/h)
Regenerant Dosage Level:	See Fig. 3
Slow Rinse (Displacement) Flow Rate:	0.30 to 0.9 US gpm/ft ³ (2 to 7 BV/h)
Fast Rinse (Displacement) Flow Rate:	1 to 5 US gpm/ft ³ (8 to 40 BV/h)
Rinse Water Requirements:	25 to 75 US gpm/ft ³
Exchange Capacity:	See Fig. 3
Reversible Swelling Na ⁺ to H ⁺	5% maximum

C-800H MP Features

Macroporous Structure

The macroporous structure of Aldex C-800H MP make it possible to incorporate a higher level of divinylbenzene into the copolymer matrix than is possible with standard gel type resins. This results in a resin which has greater stability when exposed to oxidizing conditions such as high temperatures, iron and the presences of oxidizing agents.

High Physical Stability

The macroporous structure with high divinylbenzene content provides greater resistance to bead breakage.

Safety Information

A material safety data sheet is available for Aldex C-800H MP. Copies can be obtained from Aldex Chemical Co., LTD. Aldex C-800H MP is not a hazardous product and is not WHMIS controlled.

Caution: Acidic and basic regenerant solutions are corrosive and should be handled in a manner that will prevent eye and skin contact. Before using strong oxidizing agents in contact with ion exchange resin, consult sources knowledgeable in the handling of these materials.



Since 1976

aldexchemical.com

C-800H MP Macroporous Strong Acid Resin Hydrogen Form

Pressure Drop




Fig. 1 Pressure Drop vs Flow Rate at various degrees Fahrenheit (F°)

Capacity Data

Regeneration level lbs HCl per cubic foot	Capacity kgr as CaCo ₃ per cubic foot	Influent Water
4	20.5	300 ppm ash 50% Sodium 50% Alkalinity
6	22.0	
8	23.5	
10	24.5	

Fig. 3 Capacity Data

Backwash Characteristics

Aldex C-800H MP should be backwashed for at least 10 minutes at a flow rate sufficient to cause 50% to 75% expansion of the resin bed.




Fig. 2 Hydraulic expansion data parameter flow rate GPM / FT²



Aldex Chemical Company, Ltd. • 630 Laurent Street • Granby QC Canada J2G 8V1
450 372 8844 • Fax 450 372 2566 • info@aldexchemical.com

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However, we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents. Further, we assume no liability for the consequences of such actions.